

## Mechanism for aprotic sodium-air batteries





Schematic illustration of the mechanism of proton phase-transfer catalysis. a, In ORR, oxygen is reduced at the surface to form superoxide and reacts with trace



water to form soluble HO2. The latter undergoes metathesis with Na+, driven by the free energy of formation of crystalline NaO2, to form cubic nuclei that crystallize from solution. Growth of the NaO2 from solution to form micrometre-sized cubes occurs via epitaxial growth promoted by phase-transfer catalysis of the superoxide from solution to the solid. b, OER is the reverse process: protons in solution react with the surface of the NaO2 cubes to generate HO2, releasing Na+ into the electrolyte. The soluble HO2 is transported to the carbon surface, where it is oxidized to O2. Credit: Chun Xia, et al. *Nature Chemistry*, doi:10.1038/nchem.2260

The automobile industry has been interested in finding batteries that allow electric cars to travel at a comparable distance to gas-powered cars. Currently, electric cars use a lithium ion battery, but there is interest in a metal battery that uses air as the cathode because the battery would not need to house the cathode solution. Originally, researchers focused on lithium-air batteries because energy density is similar to gasoline. However, several technical barriers have stymied progress with lithium-air batteries.

Now researchers are turning to sodium-air batteries, which have a lower energy density, but are still better than <u>lithium-ion batteries</u> in many respects. Sodium-air batteries do not have some of the technical issues that <u>lithium-air batteries</u> do, giving the sodium-air batteries a longer lifespan. As part of an effort to understand the difference between lithium- and sodium-air batteries, Chun Xia, Robert Black, Russel Fernandes, Brian Adams, and Linda F. Nazar of the University of Waterloo discovered the role of a phase transfer catalysts in the sodium-air battery reaction mechanism. Their studies were recently published in *Nature Chemistry*.

In sodium-air batteries, the sodium is the anode and the cathode is a porous carbon that traps molecular oxygen. The battery undergoes two



stages, charge and discharge. When the battery is discharged (i.e., no potential is added to the system), the sodium is oxidized, forming sodium ion (Na<sup>+</sup>). The sodium cation travels through the electrolyte and meets up with the accompanying electron passed through the external circuit that reduces the adsorbed  $O_2$ . This forms NaO<sub>2</sub>, which can be reversibly reduced back to Na<sup>+</sup> and  $O_2$ .

In <u>lithium batteries</u>,  $LiO_2$  forms  $Li_2O_2$  along with carbonate decomposition products when  $LiO_2$  reacts with the organic electrolyte. These by-products increase the charging voltage of the lithium-air battery because they cannot be easily reversibly oxidized. The voltage for charging  $Li_2O_2$  is also high, which exacerbates electrolyte decomposition. Sodium batteries, on the other hand, form less of these by-products and do not undergo subsequent reactions to form  $Na_2O_2$ . Prior studies have shown that  $NaO_2$  is stable at the nanoscale, although  $Na_2O_2$  is more stable at the bulk level. The current study shows why  $NaO_2$  is the preferred product in the sodium-air battery and why the cell can be charged so much more easily than a lithium-air cell.

Researchers know that after discharge in a sodium-air battery,  $NaO_2$  crystals form on cathode. Xia, et al. demonstrate that this process is almost exclusively driven by the presence of a proton phase-transfer catalyst (PPTC). The effects of the PPTC were tested by comparing the sodium-air battery capacity and  $NaO_2$  crystal formation in pure anhydrous sodium triflate and in sodium triflate with the addition of water as a source of protons. Their results showed that when a trace amount of water was added to the electrolyte, the discharge capacity of the battery greatly increased compared to when there was no water present, and  $NaO_2$  crystals formed. This effect increased as more water was added up to 100ppm until the effect started declining, indicating catalytic behavior.

This study also showed that oxygen evolution was almost zero in the



anhydrous environment but remained constant when water was added to the system, the PPTC is vital to oxygen evolution on charge, and hence reversibility..

Xia, et al. show that the mechanism at work in the sodium-air battery relies on the PPTC. After discharge, oxygen is reduced to a superoxide which reacts with  $H_2O$  to yield  $HO_2$  and  $OH^-$ .  $HO_2$ , which is a soluble intermediate, desorbs from the electrode surface and reacts with Na<sup>+</sup> to form nuclei of NaO<sub>2</sub>, prompting crystal growth. The formation of NaO<sub>2</sub> from HO<sub>2</sub> causes the catalyst, H<sup>+</sup>, to be released to then react with more superoxide on the cathode surface. This mechanism was confirmed using rotating disk electrode studies.

More importantly, Xia, et al. tested the reverse reaction, or the <u>battery</u> charging, as further verification that  $H^+$  is functioning as a catalyst. In the reverse reaction,  $H^+$  should react with NaO<sub>2</sub> crystals to form HO<sub>2</sub> which would then deposit superoxide on the cathode surface. They found that while the reverse reaction required prohibitively high charge potentials in an anhydrous electrolyte, the reverse reaction occurred readily in the presence of water. This study demonstrates that the equivalent catalyzed reactions cannot occur in the Lithium-air cell because the forward and reverse directions follow a different pathway.

Areas of further research would address the reactivity of  $HO_2$ , which can undergo side reactions with an organic <u>electrolyte</u>. Also, the formation of NaO<sub>2</sub> crystals may form at locations other than cathode. However, both of these factors may be overcome with further improvements to the sodium-air cell.

**More information:** "The critical role of phase-transfer catalysis in aprotic sodium oxygen batteries" *Nature Chemistry*, <u>DOI:</u> <u>10.1038/nchem.2260</u>



## Abstract

In the search for improved energy storage, rechargeable metal–oxygen batteries are very attractive owing to their reliance on molecular oxygen, which forms oxides on discharge that decompose reversibly on charge. Much focus has been directed at aprotic Li–O2 cells, but the aprotic Na–O2 system is of equal interest because of its better reversibility. We report here on the critical role and mechanism of phase-transfer catalysis in Na–O2 batteries. We find that it is solely responsible for the growth and dissolution of micrometre-sized cubic NaO2 crystals and for the reversible cell capacity. In the absence of phase-transfer catalysis, quasi-amorphous NaO2 films are formed and cells exhibit negligible capacity. Electrochemical investigations provide a measure of the transportation of superoxide from the carbon electrode to the electrolyte phase by the phase transfer catalyst. This leads to a new understanding of the mechanism of Na–O2 batteries that, significantly, extends to Li–O2 cells and explains their different behaviour.

## © 2015 TechXplore

Citation: Mechanism for aprotic sodium-air batteries (2015, May 29) retrieved 4 May 2024 from <u>https://techxplore.com/news/2015-05-mechanism-aprotic-sodium-air-batteries.html</u>

This document is subject to copyright. Apart from any fair dealing for the purpose of private study or research, no part may be reproduced without the written permission. The content is provided for information purposes only.