

## Nuclear fuel alternatives after Fukushima have challenges ahead

November 13 2019



Credit: CC0 Public Domain

Research at The University of Manchester suggests that the preferred candidate fuel to replace uranium oxide in nuclear reactors may need further development before use.

Dr. Robert Harrison led the research, published in the journal Corrosion



*Science*, with colleagues from the University and the Dalton Nuclear Institute.

"Since the 2011 Fukushima accident," explains Dr. Harrison, "there has been an <u>international effort</u> to develop accident tolerant fuels (ATFs), which are uranium-based fuel materials that could better withstand the accident scenario than the current fuel assemblies."

One of these ATFs is a uranium silicon compound,  $U_3Si_2$ . This material conducts heat much better than the traditional uranium oxide fuels, allowing the reactor core to be operated at lower temperatures. In an <u>emergency situation</u>, this buys more time for engineers to bring the reactor under control.

However, there are many unknowns about how  $U_3Si_2$  will behave in the reactor core. "One of these unknowns," says Dr. Harrison, "is how it will behave when exposed to high temperature steam or air, as may happen during manufacturing or a severe accident during reactor operation."

To investigate just how accident tolerant ATFs are, Dr. Harrison and his colleagues investigated how  $Ce_3Si_2$ —a non-radioactive material analogous to  $U_3Si_2$ —behaved under exposure to high-temperature air.

Using advanced electron microscopy techniques, available at The University of Manchester Electron Microscopy Centre (EMC), the researchers were able to study the reaction products after  $Ce_3Si_2$  was exposed to air at temperatures of up to 750°C.

They discovered the material was prone to forming nanometer sized grains of silicon and silicon oxide, as well as cerium oxide. These nanograins may allow for enhanced corrosion of the fuel material or the escape of radioactive gases formed during <u>reactor</u> activity.



This is because the formation of nanograins creates more grain boundary areas—interfaces between grains, which provide pathways for corrosive substances or fission gases to migrate along.

"Similarly," adds Dr. Harrison, "it would also allow for hazardous gaseous fission products produced during the splitting of uranium (such as xenon gas that would normally be trapped within the material) to diffuse out along these grain boundaries and be released, which would be potentially harmful to the environment."

While Dr. Harrison stops short of saying that these ATFs are more unsafe under accident conditions than the current fuels they are looking to replace, he would argue they are currently not any better, and "aren't as tolerant to accident conditions as once hoped".

Dr. Harrison concludes "However, with the new insight developed in this work it will be possible to develop and engineer ATF candidates to better withstand these accident conditions, perhaps by adding other elements, such as aluminum, or manufacturing composite materials to give higher protection of the <u>fuel</u> material".

The paper was published online on 9 November in the journal *Corrosion Science*. The title of the paper is "Atomistic Level Study of  $Ce_3Si_2$  Oxidation as an Accident Tolerant Nuclear Fuel Surrogate."

**More information:** R.W. Harrison et al. Atomistic Level Study of Ce<sub>3</sub>Si<sub>2</sub> Oxidation as an Accident Tolerant Nuclear Fuel Surrogate, *Corrosion Science* (2019). DOI: 10.1016/j.corsci.2019.108332

Provided by University of Manchester



Citation: Nuclear fuel alternatives after Fukushima have challenges ahead (2019, November 13) retrieved 6 May 2024 from

https://techxplore.com/news/2019-11-nuclear-fuel-alternatives-fukushima.html

This document is subject to copyright. Apart from any fair dealing for the purpose of private study or research, no part may be reproduced without the written permission. The content is provided for information purposes only.